

IN THE CLAIMS:

---

Claim 1. (Currently Amended) A spunbond fabric having excellent softness and strength, made from the spunbond process, including:

(a) extruding filaments composed of at least one component of an ultra low viscosity PP polypropylene polymeric resin having a ~~MFR~~ melt flow rate in grams/10 minutes at 230 degrees Centigrade greater than ~~100~~ 200 from a spinneret;

(b) drawing said filaments through a drawing unit;

(c) generating a filament speed above 4,000 meters per minute; and

(d) creating a fabric of at least one layer from said filaments drawn from said drawing unit.

A2

Claim 2. (Original) A spunbond fabric as in claim 1, including the additional step of:

(e) creating a multiple layer composite fabric containing the layer of said filaments received from said drawing unit.

Claim 3 (Original) A spunbond fabric having excellent softness, strength, barrier properties and air breathability made from the spunbond process, including:

(a) extruding filaments composed of at least one component of polyethylene terephthalate resins with IV (intrinsic viscosity) of less than 0.55 from a spinneret;

(b) drawing said filaments through a drawing unit;

(c) generating filament speeds above 4,000 meters per minute; and

- (d) creating a fabric from at least one layer of said filaments.

Claim 4. (Original) A spunbond fabric as in claim 3, including the step of:

providing additional layers of filaments on said one layer of filaments to create a multiple layer composite fabric therefrom.

AI  
Cout  
Claim 5. (Currently Amended) A spunbond fabric having excellent softness, strength, barrier properties, and air breathability made from a spunbond process, including:

- (a) extruding filaments composed of at least one component of polyamide (PA6 nylon 6) of R.V. (relative viscosity) below 2.2 from a spinneret;
- (b) drawing said filaments through a drawing unit;
- (c) generating a filament speed above 4,000 meters per minute; and
- (d) forming a fabric of at least one layer from said filaments drawn from said unit.

Claim 6. (Original) A spunbond fabric as in claim 5, including the additional step of:

- (e) creating a multiple layer composite fabric containing the layer of said filaments received from said drawing unit.

Claim 7. (Currently Amended) A spunbond fabric having excellent softness, barrier properties, and air breathability made from a spunbond process, including:

- (a) extruding filaments composed of at least one component of polyethylene resin

with a mass flow rate MFR over 50 200 grams/10 minutes at 230 degrees Centigrade from a spinneret;

- (b) drawing said filaments through a drawing unit; and
- (~~dc~~) forming a fabric of at least one layer from said filaments drawn from said unit.

A2  
Cub

Claim 8. (Currently Amended) A spunbond fabric as in claim 7, including the additional step of:

- (ed) creating a multiple layer composite fabric containing the layer of said filaments received from said drawing unit.
-